

TECHNICAL DATASHEET



EVA

SN1833ELH

Item	Test results Unit	Inspection Method
Melt mass flow rate	18 g/10min	ExxonMobil
VA contents	33 wt%	ExxonMobil
Density	0.955 g/cm ³	GB/T 1033.1-2008
Hardness	65 Shore A	GB/T 2411-2008
Tensile breaking stress	7.5 MPa	GB/T 1040.2-2006
Elongation at Break	1000 %	GB/T 1040.2-2006
Melting temperature	62 °C	ASTM D3418

Product Packaging

25kgs Bag
