

TECHNICAL DATASHEET



EVA

SN7360ETS

Properties	Typical Value Unit	Test Method
Melt Index MI _{2.16}	2.5 g/10min	ASTM D1238
Density	0.941 g/cm ³	ASTM D1505
Vinyl Acetate content	21 %	FPC method

Thermal	Typical Value Unit	Test Method
Melting point	80 °C	DSC
Brittleness point	<-70 °C	ASTM D746
Softening point	58 °C	ASTM D1525

Mechanical	Typical Value Unit	Test Method
Tensile strength at yield	40 Kg/cm ²	ASTM D638
Tensile strength at break	180 Kg/cm ²	ASTM D638
Elongation at break	800 %	ASTM D638
Hardness	86 Shore A	ASTM D2240
Hardness	36 Shore D	ASTM D2240

Product Packaging

25kgs Bag/FIBC
